

EN: This Datasheet is presented by the manufacturer.

Please visit our website for pricing and availability at www.hestore.hu.



TECHNICAL DATA

Scapa 2504

PIB Self-Amalgamating Tape

DESCRIPTION

Scapa 2504 is a general-purpose insulating, self-amalgamating tape based on PIB (Polyisobutylene) rubber. Its colour is black.

APPLICATIONS

- For jointing and repairing a wide range of power and distribution cables up to 46 kV.
- For making watertight seals at polyethylene sleeve joints on polyethylene-sleeved telephone cables both above and below ground.
- For protection against corrosion at welds and joints and for the waterproofing of many electrical components.
- For general-purpose protection and waterproofing.
- For insulation, waterproofing and protection of electrical components.
- For corrosion protection of metal pipework.
- For protection of joints against seawater in marine environments.
- For general-purpose DIY temporary repairs.
- For waterproofing and protecting cables and components on satellite dishes.

PRODUCT BENEFITS

- Good physical and electrical properties with a high degree of stability under conditions of use.
- The tape amalgamates rapidly when applied under tension to provide a void-free homogeneous wrapping, without the need for external heat or pressure.
- Compatible with a wide range of rubber and plastic dielectric cable insulation. These include polyethylene, cross-linked polyethylene, ethylene propylene rubber, PVC, butyl and neoprene.
- Compatible with other Scapa electrical tapes, including PVC tapes.
- Highly resistant to prolonged immersion in water and has excellent resistance to ozone.
- The product can be removed cleanly from most substrates, making it suitable for temporary repairs.
- Service temperature -40 to +90°C.
- Supplied in an easy to handle and apply tape form. The product is interleaved with a disposable plastic liner.

lssue: 6 Date: 24/04/03 Page 1 of 2 2504.doc

www.scapa.com

The information supplied is accurate to the best of Scapa's knowledge and is based upon all current data available to it. Properties quoted are typical and do not therefore constitute a specification. Customers must complete their own assessment of the product for its intended application under their own conditions. Our technical advice is to be regarded as an expression of opinion only and although such advice is given in good faith, it shall not, in any circumstances, be regarded as the basis of or as being a representation or statement of fact. This applies also where propriety or protective rights of third parties are involved. Any liability arising in respect of our products will be strictly limited to the value of those products charged to the customer and shall not extend to any consequential loss whatsoever and howsoever arising. Freedom from Patent Rights must not be assumed. This document does not form part of any contract with a customer.

TECHNICAL PROPERTIES

	Unit	Nominal Value	Test Method
Thickness	mm	0.75	
Tensile Strength	MPa	2	BS 903
Elongation at Break	%	900	BS 903
Volume Resistivity	Ohm.m	1 x 10 ¹³	ASTM D257
Dielectric Strength	kV/mm	42	ASTM D149

STANDARD PRESENTATION

Roll length: 3m, 5m, 10mRoll width: 19mm, 25mm

Core: 38mm dense plastic

Packaging: Individually shrink-wrapped rolls

Branding: Scapa

RECOMMENDATIONS

Care should be taken to avoid direct contact between the tape and petroleum-type solvents and oils. Oils may affect the electrical properties of the tape.

The rolls should be stored flat on their cut edges in the original packaging. The product must be protected from dust, heat, moisture, direct sunlight and solvent fumes. Storage temperature between +10°C and +30°C. Under these conditions, the storage life of the tape in a temperate climate will be at least one year.

Issue : 6 Date : 24/04/03 Page 2 of 2 2504.doc

www.scapa.com