EN: This Datasheet/Document is presented by the manufacturer.

Please visit our website for pricing and availability at www.hestore.hu.

CHIPQUIK® RMA591-5M

Datasheet revision 1.1 www.chipquik.com

ROL0 RMA Tack Flux (for Leaded) in 5cc/5g Luer Lock Manual Syringe w/tips

Product Highlights

Tack Flux Rosin Mildly Activated (RMA)
Used for touch up and rework,
attachment of BGA spheres, and
soldering flip chip components.
Low viscosity synthetic
RoHS 3 and REACH compliant



Representative Photo Only
Please note flux color may vary
from light yellow to orange/brown

Specifications

Flux Type:	Synthetic RMA (for Leaded applications)
Flux Classification:	ROL0
Flux Activation Temperature:	140°C (284°F)
Color:	Light yellow to orange/brown
Packaging:	5cc/5g Luer Lock Manual Syringe
Shelf Life:	Refrigerated >24 months, Unrefrigerated >24 months

Stencil Life

>8 hours @ 20-50% RH 22-28°C (72-82°F)
>4 hours @ 50-70% RH 22-28°C (72-82°F)

Stencil Cleaning

Automated stencil cleaning systems for both stencil and misprinted boards. Manual cleaning using isopropyl alcohol (IPA).

Storage and Handling

Store refrigerated or at room temperature 3-25°C (37-77°F). Do not freeze. Allow 4 hours for flux to reach an operating temperature of 20-25°C (68-77°F) before use.

Transportation

This product has no shipping restrictions. Shipping below 0°C (32°F) or above 25°C (77°F) for normal transit times by ground or air will not impact this product's stated shelf life.

Conforms to the following Industry Standards:

J-STD-004B, Amendment 1 (Solder Fluxes):	Yes
RoHS 3 Directive (EU) 2015/863:	Yes

© 1994-2023 Chip Quik® Inc.