EN: This Datasheet/Document is presented by the manufacturer.

Please visit our website for pricing and availability at www.hestore.hu.

TermoPasty®
Termopasty Grzegorz Gąsowski
ul. Kolejowa 33 E, 18-218 Sokoły, tel. 86 274 13 42, fax 86 274 13 50
PKO BP S.A. 96 1020 1332 0000 1502 0324 0447
NIP: 966-176-77-14, REGON: 200133730
www.termopasty.pl, e-mail: biuro@termopasty.pl

SPECIFICATION

Product : **AG TermoGlu**

Weight : **10 g / 120 g**

	Property	
1.	Color	White
2.	Surface Drying Time [25°C, min]	2 – 8
3.	Hardness (Shore A)	45–75
4.	Tensile Strength (Mpa)	2.0
5.	Elongation (%)	100
6.	Thermal Conductivity (W/mk)	> 1.0
7.	Volume Resistance (c-in/W)	$< 2.0 \times 10^{15}$
8.	Dielectric strength (KV/mm)	20
9.	Dielectric Constant	3.0
10.	Dielectric loss factor (60 Hz)	0.003
11.	Continuous Use Temp (max)	200°C

Storage and use :

1. Before application clean the contact surface.
2. Apply the thinnest possible layer of the glue. Do not exceed 6 mm.Product working temperature from -50 to 200°C.
3. AG TermoGlue should dry out completely after 24 hours. However, depending on the applied thickness, the glue may set for up to 2 days.
4. Make sure to tightly close the packaging, if the product is not used at one time.

Avoid contact with eyes. The product is non-toxic. Store it in a cool and dry place for up to 12 months